

## **IN THE CLAIMS**


This listing of claims replaces all prior versions, and listings, in this application.

Claims 1-10 (Canceled).

11. (Currently Amended) A one step process for the preparation of a metal-organic compound, comprising contacting at least one imine ligand according to formula 1 with a metal-organic reagent of formula 2 in the presence of at least 1 equivalent of an inorganic or metal-organic base, or wherein an HA adduct of the imine ligand is contacted with a metal-organic reagent of formula 2 in the presence of at least 2 equivalents of an inorganic or metal-organic base, wherein formula 1 is:



wherein Y is selected from a substituted carbon, nitrogen, or phosphorous atom and R represents a proton, a protic or an aprotic substituent, and formula 2 is:



wherein:

M represents a group 4 or group 5 metal ion,

V represents the valency of the metal ion, which is 3, 4 or 5,

L<sub>1</sub>, L<sub>2</sub>, L<sub>3</sub>, and L<sub>4</sub> represent ligands on M which may be the same or different,


X represents a group 17-halogen atom,

k, l, m, n = 0, 1, 2, 3, 4 with k+l+m+n+1=V, and

wherein HA represents an acid, of which H represents its proton and A its conjugated base.


12. (Currently Amended) A process according to claim 11 wherein R represents a hydrogen atom and Y is selected from the group consisting of:

(i) a phosphorus substituent defined by the formula:




(formula 3)

wherein each  $R^{1j}$ , with  $j = 1-3$ , is independently selected from the group consisting of a hydrogen atom, a halogen atom, a  $C_{1-8}$  alkoxy radical, a  $C_{6-10}$  aryl or aryloxy radical, an amido radical, a  $C_{1-20}$  hydrocarbyl radical unsubstituted or substituted by a halogen atom, a  $C_{1-8}$  alkoxy radical, a  $C_{6-10}$  aryl or aryloxy radical, an amido radical, a silyl radical of the formula:



(formula 4)


and a germanyl radical of the formula:



(formula 5)

wherein  $R^{2j}$  is independently selected from the group consisting of hydrogen, a  $C_{1-8}$  alkyl or alkoxy radical, or a and  $C_{6-10}$  aryl or aryloxy radicals radical, provided each substituent  $R^{1j}$  or  $R^{2j}$  may be linked with another  $R^1$  or  $R^2$  to form a ring system, and

(ii) a substituent defined by formula 6:



(formula 6)

wherein each of Sub<sup>1</sup> and Sub<sup>2</sup> is independently selected from the group consisting of hydrocarbonyl radicals having from 1 to 30 carbon atoms; silyl radicals, substituted or unsubstituted amido radicals and substituted or unsubstituted phosphido radicals, and wherein Sub<sup>1</sup> and Sub<sup>2</sup> may be linked with each other to form a ring system.

13. (Withdrawn) A process according to claim 11, wherein the base is a carboxylate, or a fluoride, or a hydroxide, or a cyanide, or an amide, or a carbonate of Li, Na, K, Rb, Cs, or a group 2 metal salt selected from Mg, Ca, or Ba, or an alkali metal selected from Li, Na, K, Rb, or Cs of a phosphate or a phosphate ester, or alkoxide of Li, Na, K, Rb or Cs or a phenoxide of Li, Na, K, Rb or Cs, or thallium hydroxide, or a hydrocarbanion of any of the group 1, group 2, group 12 or group 13 elements, or an alkali metal, group 1 hydride or group 2 hydride.

14. (Withdrawn) A process according to claim 13, wherein the inorganic base is selected from sodium hydride, or calciumhydride.

15. (Previously Presented) A process according to claim 11, wherein the metal-organic base is selected from an organolithium compound, or an organomagnesium compound.

16. (Previously Presented) A process according to claim 11, wherein the reaction is carried out in an aprotic solvent.

17. (Withdrawn) A process according claim 11, wherein the process is carried out in the presence of a phase transfer reagent.

18. (Previously Presented) A process for the preparation of a polyolefin by preparing a metal-organic compound according to the process of claim 11, wherein the base is an olefin polymerization-compatible base, wherein the metal-organic compound is activated anywhere in, or before a polymerization reactor.

19. (Previously Presented) A process according to claim 18, wherein the metal-organic compound is used without purification.

20. (Previously Presented) A process according to claim 18, wherein the metal-organic compound is formed in the polymerization reactor.